

# Dow Corning® TC-2030 Thermally Conductive Adhesive

Two-part, heat cured thermally conductive adhesive

## Material Properties

### Description

Dow Corning® TC-2030 is a two-part thermally conductive adhesive with thermal conductivity of 2.7 W/mK. TC-2030 uses field-proven, reliable alumina fillers to new levels of loading, rheology and bondline control to achieve a step-change in elongation and thermal performance stability after aging. TC-2030 was specifically developed for a broad-industry need for heat dissipation at medium to large bond line thickness (BLT). Minimum BLT is approximately 150 µm. Dow Corning has extensive experience in processing this material and can provide valuable customer support.

### Key Features

- Thermal conductivity: 2.7 W/mK
- Excellent performance at medium to high BLT
- Mechanical reliability – maintains stable elongation after accelerated aging tests
- Adhesive reliability – adhesion stays stable or improves after accelerated aging
- Thixotropic for accurate needle dispense
- Adhesion to various substrates

### Potential Uses

Thermal interface material for a variety of electronic devices

### Typical Applications

- Lid sealant
- LED assembly attach
- High power modules
- Under hood automotive electronics
- Power steering, antilock braking and electronic stability control modules

### Application Method



- Automated or manual needle dispense

Property	Dow Corning® TC-2030 Thermally Conductive Adhesive
Description	Thermally conductive adhesive
Form	Two-part, heat cure
Mix ratio	1:1
Viscosity Part A	210,000 cP
Viscosity Part B	180,000 cP
Viscosity mixed	190,000 cP
Specific gravity	2.9
Thixotropy	1.8
Working time – viscosity after 4 hours @ 25°C	230,000 cP
Tensile strength	655 psi
Heat cure time at 130°C	60 minutes
Elongation	45%
Durometer Shore A	90
Unprimed adhesion (lap shear to aluminum)	410 psi
Thermal conductivity	2.7 W/mK
Volume resistivity	1.3 E+13 ohm*cm
Dielectric strength	525 volts/mil

## Important Features and Benefits

Features	Benefits
High thermal conductivity	<ul style="list-style-type: none"> <li>• Reduced thermal resistance</li> <li>• Performance at medium to thick bond lines (150µm)</li> </ul>
Stable elongation	<ul style="list-style-type: none"> <li>• High reliability</li> <li>• No cracking, maintains structural integrity and thermal transfer properties</li> </ul>
Adhesion to various substrates	Adheres to: <ul style="list-style-type: none"> <li>• Anodized aluminum</li> <li>• Cast aluminum</li> <li>• Tin plated copper</li> <li>• Copper</li> <li>• Printed circuit board</li> <li>• Others</li> </ul>

## Performance Data



## Need Additional Help?

Dow Corning offers a broad range of thermal products and solutions to meet your current and emerging needs.

For additional information on the complete line of *Dow Corning*<sup>®</sup> brand thermal management products, please call your local sales office, see [www.dowcorning.com/electronics](http://www.dowcorning.com/electronics), or e-mail [electronics@dowcorning.com](mailto:electronics@dowcorning.com).

## Your Global Connection

### Asia

Dow Corning Toray Silicone Co., Ltd. – Japan  
Tel: +81 3 3287 1011 (Tokyo Office)  
Dow Corning Korea Ltd. – Seoul  
Tel: +82 2 551 7600  
Dow Corning Taiwan Inc. – Taipei  
Tel: +886 2 6600 3100  
Dow Corning China – Shanghai  
Tel: +86 21 2306 5500  
Dow Corning – Malaysia  
Tel: +60 3 5032 2128  
Dow Corning Asia – Singapore  
Tel: +65 6359 3331  
Dow Corning (Thailand) Ltd. – Thailand  
Tel: +65 6359 3331

### Europe

Dow Corning S.A.  
Tel: +32 64 888 000

### North America

Dow Corning Corporation  
World Headquarters  
Tel: +1 989 496 6000

### South America

Dow Corning Do Brasil Limitada  
Tel: +55 11 3759 4300

Front images: AV03137, AV02251

### LIMITED WARRANTY INFORMATION—PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

*Dow Corning* is a registered trademark of Dow Corning Corporation.

*We help you invent the future* is a trademark of Dow Corning Corporation.

©2009 Dow Corning Corporation. All rights reserved.

AMP026-09

Form No. 11-1742-01

**DOW CORNING**

**Electronics**  
Solutions

*We help you invent the future.™*