

**Formulation Information**  
New Skin Care Applications



## IlluminEyes

### Make-up Base: Anti-ageing Cosmetic, Silky gel

Formulation 00704

#### ATTRIBUTES

- Good spreadability
- Luxurious, dry, light feel
- Very comfortable to wear
- Anti-ageing Cosmetic
- Silky gel

#### DOW CORNING® PRODUCTS

- Dow Corning® 245 FLUID
- Dow Corning® 5200 FORMULATION AID
- Dow Corning® 5562 CARBINOL FLUID
- Dow Corning® 9546 SILICONE ELASTOMER BLEND
- Dow Corning® BY 11-030

Ingredient	Wt. %	Trade Name/Supplier
<b>Phase A</b>		
1. Cyclopentasiloxane (and) Dimethicone Copolyol	16	Dow Corning® BY 11-030
2. Cyclopentasiloxane	29.9	Dow Corning® 245 FLUID
3. Isononyl Isononanoate	3.7	DUB ININ / Stearinerie Dubois Fils
4. Cyclopentasiloxane (and) Dimethicone Crosspolymer (and) Dimethicone/Vinyl Dimethicone Crosspolymer (and) Dimethiconol	12.3	Dow Corning® 9546 SILICONE ELASTOMER BLEND
5. Lauryl PEG/PPG-18/18 Methicone	1.2	Dow Corning® 5200 FORMULATION AID
6. Phenoxyethanol (and) Methylparaben (and) Ethylparaben (and) Butylparaben (and) Isobutylparaben (and) Propylparaben	0.5	Dekaben / Jan Dekker
7. Perfume	0.5	Hydra / Symrise
<b>Phase B</b>		
8. Water	8.7	
9. Hydrolyzed Rice Bran Protein, Oxido Reductases, Glycine Soja Protein	4	Regu-Age / Pentapharm, CH
<b>Phase C</b>		
10. Cyclopentasiloxane	12.9	Dow Corning® 245 FLUID
11. Bis-Hydroxyethoxypropyl Dimethicone	5	Dow Corning® 5562 CARBINOL FLUID
12. Mica (and) Silica	1.44	Micronasphere M / Merck KGaA
13. Titanium Dioxide (and) Mica	0.3	Timiron Silk Gold / Merck KGaA
14. Titanium Dioxide	2.86	Oxyde De Titane Organophile W 877 / LCW Sensient
15. Iron Oxides Yellow	0.7	Covasil 3.05 Yellow W 1802 / LCW Sensient

#### Procedure

1. Prepare a pigment premix by blending phase C ingredients and homogenize until a uniform color is obtained.
2. Mix phase A except DC 9546 and stir using moderate speed until BY 11-030 is completely dissolved.
3. Add the pigment premix and stir until homogeneous.

4. Add ingredient 4 while mixing and increasing speed. Mix until homogeneous.
5. Mix Phase B ingredients together and add to Phase A with mixing.
6. Be aware that the mixture will fastly develop high viscosity.
7. Continue mixing for an additional 5 minutes.

**Variations**

Alternative Dow Corning® Products have not been tested as of this printing.

**Stability**

Stable for at least 6 months at room temperature and 6 months at 40 C.

**External Reference Material**

No external references identified as of this printing.

**Dow Corning® Application Patents**

---

Dow Corning hopes that this suggested formulation will be of interest to you, but you should be cautioned that this is only a representative formulation and is not a commercialized product. Dow Corning believes that the information and data on which this formulation is based are reliable, but it has not been subjected to extensive testing for performance, efficacy or safety. In addition, Dow Corning has not undertaken a comprehensive patent search on the formulation. BEFORE COMMERCIALIZATION, YOU SHOULD THOROUGHLY TEST THE FORMULATION OR ANY VARIATION OF IT TO DETERMINE ITS PERFORMANCE, EFFICACY AND SAFETY. IT IS YOUR RESPONSIBILITY TO OBTAIN ANY NECESSARY GOVERNMENT CLEARANCE, LICENSE OR REGISTRATION. Suggestions of uses should not be taken as inducements to infringe any particular patent.

**SAFE HANDLING INFORMATION**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE FROM YOUR DOW CORNING REPRESENTATIVE, OR DISTRIBUTOR, OR BY WRITING TO DOW CORNING CUSTOMER SERVICE, OR BY CALLING (989) 496-6000.

*Dow Corning* is a registered trademark of Dow Corning Corporation.  
Copyright 1999 Dow Corning Corporation. All rights reserved.

Print Date: 7/28/2006

Last Updated: 6/21/2005 12:26:01 PM